

January, 2019

3M™ VentureClad™ Insulation Jacketing System 1577CW

Product Description

3M™ VentureClad™ Insulation Jacketing System is a zero permeability, all weather, multi-layered laminate coated with an aggressive cold weather acrylic adhesive. Superior resistance to weathering, fungi, UV and extreme environmental conditions. Designed for use as a vapor barrier for insulation cladding and jacketing applications. Available in both flat and embossed.

Product Features

- Superior adhesion in cold or hot and humid conditions temperatures.
- Bonds and seals at temperatures as cold as -10°F (-23°C).
- Zero permeability vapor barrier for insulation cladding and jacketing applications
- High puncture and tear resistant ensures longevity and durability
- Flexible and strong.
- Cuts and installs easily on-site, no special tools required.
- Available in multiple colors.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Method
Color	Natural Aluminum		
Total Tape Thickness without liner	0.16 mm	6 mil	
Embossed	No		
Puncture	111 N	25 lb	
Water Vapor Transmission	0.00 Perms		ASTM E96

Typical Performance Characteristics

Property	Values	
Peel Adhesion	8.2 N/cm	75 oz/in
Tensile Strength	140 N/cm	80 lb/in
Emittance	0.03	
Service Temperature Range	-70 to 149 °C	-94 to 300 °F

Typical Environmental Performance

Chemical Resistance: Good

3M™ VentureClad™ Insulation Jacketing System 1577CW

Certifications

Product	1577CW	1577CW-E	1577CW-WM	1577CW-WME
ASTM E84 Flame/Smoke Rating			25/45	25/45
UL723 Classified Flame/Smoke Rating (UL file #R10984)	25/25	25/25		
CAN/ULC S102 Classification Flame/Smoke Rating	25/25	25/25	25/25	
Meets FDA Compositional requirements for indirect food contact (21 CFR 175.105 and 21 CFR 175.125; FDA: Indirect Food Additives; Adhesives and Components of coatings)			X	X
Approved by Canadian Food Inspection Agency for use in food processing facilities as vapor barrier for insulation cladding and jacketing			X	X
Contains Mold Inhibiting Agents	X	X		
Passes ASTM C1338 Fungi Resistance Testing	X	X	X	X
U.S. Coast Guard Approval	164.112/1121/WCL MED0285	164.112/1121/WCL MED0285	164.112/1121/WCL MED0290TE	164.112/1121/WCL MED0290TE
IMO Resolution A653 (16)	X	X	X	X
IMO Resolution MSC61 (67) Annex 2 IMO Resolution MSC 61 (67) Annex 1 Part 2 and Annex 2	X	X	X	X
BS476 parts 6 & 7 Class "O"	X	X	X	X
DIN 4102-1	X	X		
SANS 10177 Opart 3 Class 1	X	X		
NYC MEA	X	X		
Meets CINI 3.3-12 Requirement	X	X		
Japan Building Standard Law Article 2, Clause 9	X	X		
Passes ASTM C1775 Specification for Laminate Protective Jacketing for Outdoor Applications	X	X		

Storage and Shelf Life

Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40 to 50% relative humidity are recommended. To obtain best performance, use this product within 24 months from date of manufacture.

3M™ VentureClad™ Insulation Jacketing System 1577CW

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks

3M and VentureClad are trademarks of 3M Company.

References

Safety Data Sheet (SDS)

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=1577CW

Family Group

	1577CW	1577CW-E	1577CE-CM	1577CW-WM	1577CW-WME
Color	Natural Aluminum	Natural Aluminum	Natural Aluminum	White	White
Total Tape Thickness without liner (mm)	0.16	0.23	0.18	0.18	0.23

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

